

PAVUS, a.s. AUTHORIZED BODY 216

NOTIFIED BODY 1391 ACCREDITED CERTIFICATION BODY FOR PRODUCTS CERTIFICATION Nº 3041

Prosecká 412/74, CZ 190 00 Praha 9 - Prosek

Phone: +420 286 019 587

Mail to: mail@pavus.cz, http://www.pavus.cz

Branch: FIRE TESTING LABORATORY

VESELÍ NAD LUŽNICÍ Čtvrť J. Hybeše 879

CZ 391 81 Veselí nad Lužnicí

Czech Republic

Phone: +420 381 477 418 Mail to: veseli@pavus.cz

REACTION TO FIRE CLASSIFICATION REPORT

Object of classification:

Construction products excluding floorings and linear

pipe thermal insulation products in accordance with

EN 13501-1:2018, cl. 11 EN 14782:2006, Annex C EN 14783:2013, Annex B

Classification report No:

PK1-01-19-073-E-0

Product name:

Coil Coated aluminium coils & sheets

Sponsor:

Luxe Coat S.r.I.

Via degli Opifici snc

67100 Bazzano - L'Aquila (AQ)

Italia

Prepared by:

PAVUS, a.s.

Authorized body AO 216

Notified body 1391

Accredited certification body for products certification No. 3041

Accreditation issued by Czech Accreditation Institute,

Public Service, Certificate of Accreditation No. 170/2019

Prosecká 412/74 190 00 PRAHA 9 Order No. Z210190274

Date of issue:

2019-12-13

Copies in total:

3

Issue number:

Pages in total:

Page 2 of 6

1. INTRODUCTION

- 1.1. This classification report defines the classification assigned to *Coil Coated aluminium coils* & sheets in accordance with the procedures given in EN 13501-1:2018 together with the procedures given in EN 14782:2006, Annex C, resp. EN 14783:2013, Annex B.
- 1.2. This classification report consists of six pages and may only be used or reproduced in its entirety.

2. DETAILS OF CLASSIFIED PRODUCT

2.1. General

The product *Coil Coated aluminium coils & sheets* is manufactured by Luxe Coat S.r.I., Via degli Opifici snc, 67100 Bazzano - L'Aquila (AQ), Italia. It is a product in accordance with EN 14782:2006, respectively EN 14783:2013. They are continuously varnished coils and sheets from aluminium or aluminium alloy. The face side is coated with a primer and top coat, respectively top coat, a back coat is on the reverse side.

2.2. Product description

| Sheet metal | Metal | Aluminium, aluminium alloys | | | | | |
|----------------|--------------------------------------|---------------------------------|---------------------------------|-----------------------------------|---------------------------------|------------------------------------|--|
| | Thickness (mm) | from 1.0 | | | | | |
| | Density (kg/m³) | from 2,670 | | | | | |
| Types of coat | | 1. PVDF 3 Layer | 2. PVDF 2 Layer | 3. PUR-PA | 4. Polyester (SP) | 5. Polyester Powder (PPC) | |
| Primer | Туре | SP (VL 3245) ¹⁾ | SP (VL 3245) ¹⁾ | SP (VL 3245) ¹⁾ | SP (VL 3245) ¹⁾ | - | |
| | Thickness (µm) | 4 | 4 | 4 | 4 | - | |
| | Basis weight in dry condition (g/m²) | 6.7 | 6.7 | 6.7 | 6.7 | - | |
| Top coat | Туре | PVDF (VL 3531) ¹⁾ | PVDF (VL 3531) ¹⁾ | PUR-PA (VL 3092) ¹⁾ | PES (VL 3349) ¹⁾ | PPC (VP 3080) ¹⁾ | |
| | Thickness (µm) | 20 | 20 | 20 | 20 | 60 | |
| | Basis weight in dry condition (g/m²) | 37.4 | 37.4 | 35.2 | 27.2 | 78 | |
| Top coat | Туре | FEVE (VL 3339) | - | - | | - | |
| | Thickness (µm) | 10 | - | i.e. | 51 | - | |
| | Basis weight in dry condition (g/m²) | 16.8 | - | - | - | - | |
| Back coat | Туре | SP EP (VL 232) ¹⁾ | SP EP (VL 232) ¹⁾ | SP EP (VL 232) ¹⁾ | SP EP (VL 232) ¹⁾ | SP EP (VL 232) ¹⁾ | |
| | Thickness (µm) | 4 | 4 | 4 | 4 | 4 | |
| | Basis weight in dry condition (g/m²) | 5.6 | 5.6 | 5.6 | 5.6 | 5.6 | |



CLASSIFICATION REPORT No. PK1-01-19-073-E-0

Page 3 of 6

According to EN 13823+A1:2018 the 5th type of coat was tested with the following parameters:

Sheet aluminium alloy:

AlMg3, thickness of 1,0 mm, basis weight of 2,67 g/m²

Coating system:

back coat: SP EP (VL 232)¹⁾ measured average thickness of 7 μm

top coat: PPC (VP 3080)1) measured average thickness of 46 µm

1) The exact product name and the manufacturer is given in the test reports.

3. REPORTS AND RESULTS IN SUPPORT OF THIS CLASSIFICATION

3.1. Reports

| Name of Laboratory Address Accreditation No. | Name of sponsor | Report ref. No. Date of issue | Test method and date Field of application rules and date |
|--|--|----------------------------------|--|
| PAVUS, a. s. | Luxe Coat S.r.l. | Pr-19-1.214-En | EN ISO 1716:2018 |
| Veselí nad Lužnicí ATL No. 1026 | Via degli Opifici snc 67100 Bazzano - L'Aquila (AQ) Italia | 2019-11-08 | EN 14782:2006 EN 14783:2013 |
| | | Pr-19-1.215-En | EN ISO 1716:2018 |
| | | 2019-11-08 | EN 14782:2006 EN 14783:2013 |
| | | Pr-19-1.216-En | EN ISO 1716:2018 |
| | | 2019-11-08 | EN 14782:2006 EN 14783:2013 |
| | | Pr-19-1.217-En | EN ISO 1716:2018 |
| | | 2019-11-08 | EN 14782:2006 EN 14783:2013 |
| | | Pr-19-1.218-En | EN ISO 1716:2018 |
| | | 2019-11-08 | EN 14782:2006 EN 14783:2013 |
| | | Pr-19-1.218-En | EN ISO 1716:2018 |
| | | 2019-11-08 | EN 14782:2006 EN 14783:2013 |
| | | Pr-19-1.220-En | EN ISO 1716:2018 |
| | | 2019-11-08 | EN 14782:2006 EN 14783:2013 |
| | | Pr-19-1.221-En | EN 13823+A1:2018 |
| | | 2019-12-12 | EN 14782:2006 EN 14783:2013 |

Page 4 of 6

3.2. Results

| | | | Results | | |
|---|--|-----------|-----------------------------|----------------------------|--|
| Test method | Parameter | No. Tests | Continuous parameter - mean | Compliance with parameters | |
| EN 13823+A1 | FIGRA _{0.2MJ} (W/s) | | 0.0 | ≤ 20 (A1) | |
| 5 th type of coat | THR _{600s} (MJ) | | 0.5 | ≤ 4 (A1) | |
| | LFS < edge of specimen | | - | yes (A1) | |
| | SMOGRA ¹⁾ (m ² /s ²) | 3 | 1.7 | ≤ 30 (A1) | |
| | TSP _{600s} ¹⁾ (m ²) | | 34.4 | ≤ 50 (A1) | |
| | No flaming droplets/ particles | | - | yes (A1) | |
| EN ISO 1716 | | | | | |
| 1st type of coat PVDF (VL 3531) top coat + FEVE (VL 3339) top coat + SP (VL 3245) primer – external non-substantial component | PCS ²⁾ (MJ/m ²) | 3× 3 | 0.58 + 0.37 + 0.12 | - | |
| EN ISO 1716 | | | | | |
| 2 nd type of coat PVDF (VL 3531) top coat + SP (VL 3245) primer – external non-substantial component | PCS ²⁾ (MJ/m ²) | 2× 3 | 0.58 + 0.12 | v . | |
| EN ISO 1716 | | | | | |
| 3 rd type of coat PUR-PA (VL 3092) top coat + SP (VL 3245) primer – external non-substantial component | PCS ²⁾ (MJ/m ²) | 2× 3 | 0.54 + 0.12 | - | |
| EN ISO 1716 | | | | | |
| 4 th type of coat PES (VL 3349) top coat + SP (VL 3245) primer – external non-substantial component | PCS ²⁾ (MJ/m ²) | 2× 3 | 0.52 + 0.12 | - | |
| EN ISO 1716 | | | | | |
| 5 th type of coat PPC (VP 3080) top coat – external non-substantial component | PCS ²⁾ (MJ/m ²) | 3 | 1.50 | ≤ 2.0 (A1) | |
| EN ISO 1716 | | | | | |
| All types of coat SP EP (VL 232) back coat – external non-substantial component | PCS ²⁾ (MJ/m ²) | 3 | 0.12 | ≤ 2.0 (A1) | |
| EN ISO 1716 | | | | 31 | |
| Sheet metal – substantial component | PCS (MJ/kg) | 03) | 0.00 | ≤ 2.0 (A1) | |



CLASSIFICATION REPORT No. PK1-01-19-073-E-0

Page 5 of 6

| | | | Results | | |
|---------------------------------|-----------------------------------|-----------|-----------------------------|----------------------------------|--|
| Test method | Parameter | No. Tests | Continuous parameter - mean | Compliance with parameters | |
| EN ISO 1716 Product as whole | PCS (MJ/kg) | - | ≤ 0.59 | ≤ 2.0 (A1) | |
| EN ISO 1182 Sheet metal | ΔT (°C) Δm (%) t _f (s) | 04) | ≤ 30 ≤ 50 0 | ≤ 30 (A1) ≤ 50 (A1) 0 (A1) | |

The classical method of smoke calculation according to EN 13823+A1:2018, Annex A, cl. A.6.1.2 it was used.

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1. Reference of Classification

This classification has been carried out in accordance with EN 13501-1:2018.

4.2. Classification

The product Coil Coated aluminium coils & sheets in relation to its reaction to fire behaviour is classified:

Reaction to fire classification: A1

4.3. Field of application

This classification is valid for the following product parameters:

Grade of metal¹⁾: all grades of metal sheet Density of metal sheet: at least 2,670 kg/m³ Nominal thickness t_n of metal¹⁾: at least 1.0 mm

Profile geometry of sheeting: flat,

profiled or corrugated, or cassettes¹⁾: type tested only Colour¹⁾: all colours

Type of coating¹): tested coating type and where PCS and mass ≤ that of the

tested organic coatings

Back coat: basis weight in dry condition at most 10.3 g/m^{2 2)}

gross heat of combustion PCS at most 0.12 MJ/m²

Primer + top coat(s): basis weight in dry condition at most 60.2 g/m² (sum) ²⁾

gross heat of combustion PCS at most 1.50 MJ/m² (sum)

Types of coats with the stated basis weight in dry condition values according to table in cl. 2.2 of this report comply with this classification, provided that the1st type of coat will have basis weight in dry state of a primer + top coats (sum) not more than 60.2 g/m 2 1) and 5th type of coat will have basis weight of top coat not more than 60.2 g/m 2 .

²⁾ The gross heat of combustion is signed as Q_{PCS} according to EN ISO 1716:2018.

Metallic components shall not be tested. Their gross heat of combustion shall be deemed to be zero according to EN ISO 1716:2018.

⁴⁾ Product is classified as reaction to fire class A1 without testing according to Commission Decision 96/603/ES as amended Commission Decisions 2000/605/ES and 2003/424/ES.



The classification is valid for the following end use applications:

Overlap between two successive profiles1): valid for all overlaps between 40 mm and 300 mm

Horizontal joint1):

valid for end use conditions with or without this joint

Fixing for metal flashing1):

valid for all spacing less than or equal to that tested, it means for spacing at most 360 mm

- 1) With respect to EN 14782:2006, Annex C, cl. C.3.2.2, Table C.2.
- 2) With respect to the test samples.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.

This classification is valid, unless the conditions, under which it was issued, have been changed. The sponsor may request the issuing authority to review the influence of changes to the classification validity.

Elaborated by:

Ladislav Městka

Fire testing laboratory

PAVUS, a.s.

Autorizovaná osoba AO 216 Pobočka

391 81 Veselí nad Lužnicí 🖯

Approved by:

Jaroslav Dufek